

# CLAYPRO

AUST PTY LTD

PH: 03 5449 3970 FAX: 03 5449 3960

48 PRATTS PARK RD BENDIGO

## CA 1

Ball clay  
Dry milled  
very plastic  
high green strength


### Typical Analysis X.R.F

Silica SiO <sub>2</sub>	Alumina Al <sub>2</sub> O <sub>3</sub>	Iron oxide Fe <sub>2</sub> O <sub>3</sub>	Calcium CaO	Magnesium Oxide MgO	Sodium Na <sub>2</sub> O	Potassium K <sub>2</sub> O	Manganese MnO	Titanium Oxide TiO <sub>2</sub>	L.O.I
59.0	25.4	1.09	.01	.85	.23	3.00	<.01	1.40	8.40

Less Than 2% Moisture

### Particle Size Distribution

CA 1



[Back to Products](#)